

TECHNICAL DATA SHEET

TWO PACK COAL TAR EPOXY - REF: - 56L253

A high performance two pack polyamide cured Coal Tar Epoxy coating it is noted for its hardness, abrasion resistance and durability in a wide range of conditions.

PACKAGE SIZE	5 Litre, 25 Litre
COLOUR	
FLASH POINT	22°C - 32°C
DRYING TIME @ 20°C 7 Days to full cure	Surface Dry: 40 – 60 mins
VOLUME SOLIDS	60 (+/- 5%)
RECOMMENDED W.F.T.	100 - 125 microns
RECOMMENDED D.F.T.	65 - 75 microns
THEORETICAL SPREADING RATE	7-8 Sq.Mtrs/Ltr @ Average DFT assuming 100% transfer efficiency
THINNERS	50/14
SHELF LIFE	12 mths
V.O.C.	400 – 420 g/litre (mixed)

SURFACE PREPERATION

Ensure surface is free from rust, moisture, oil or other surface contamination.

CURING TIME

Temperature dependant for Full cure, 20°C for 7 days.

APPLICATION

Brush or Roller.

HEALTH & SAFETY

Refer to M.S.D.S. prior to use.

Provide adequate ventilation. Prolonged skin contact inhalation of vapour must be avoided. Eye contamination - Flush with eyewash or warm water for 10 mins. Clean hands after use.

Any person or company using this product without first making enquiries as to the suitability for the intended purpose does so at their own risk, and Fiesta Industrial Paints Ltd can accept no liability for the performance of the product or for any loss or damage arising out of such use.

FIESTA INDUSTRIAL PAINTS LTD
BURNLEY ROAD, HAPTON LANCS BB11 5QR
TEL:01282 775639/FAX:01282 776406