

# Stokes OCF Semi-Gloss (QS-QF-QC)

<b>Product Description</b>	<b>A general purpose, one coat* anticorrosive alkyd primer/finish (semi-gloss) for steel.</b>				
<b>Features &amp; Use</b>	<ul style="list-style-type: none"> <li>• For use on modular buildings, industrial machinery, metal fabrications, castings, and a wide range of engineering items</li> <li>• Designed for airless spray application</li> <li>• Excellent build properties and hold-up on edges</li> <li>• Contains zinc phosphate anticorrosive pigment</li> <li>• Good resistance to most hot and cold lubricating and cutting oils when fully cured. Tests for suitability with any particular oil should be made before large scale application</li> </ul>				
<b>Approvals/ Certification</b>	Please consult Spencer Coatings				
<b>Finish</b>	Semi-gloss				
<b>Volume Solids</b>	34 ± 3% (varies with colour)				
<b>VOC Content</b>	542 ± 30 g/litre (varies with colour)				
<b>Film Thickness Range And Coverage</b>		<b>Dry Film Thickness</b>	<b>Wet Film Thickness</b>	<b>Theoretical Coverage</b>	
	<b>Minimum</b>	90 µm	264 µm	3.7 m <sup>2</sup> /litre	
	<b>Maximum</b>	150 µm	441 µm	2.2 m <sup>2</sup> /litre	
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated					
<b>Drying Times</b>	Applied to 90 microns DFT	<b>+10°C</b>	<b>+23°C</b>	<b>+35°C</b>	
	<b>Dust Free</b>	1 hr	30 min	15 min	
	<b>Hard Dry</b>	4 hr	2 hr	1 hr	
	<b>Overcoating</b>	Minimum	4 hr	2 hr	1 hr
		Maximum	Indefinite if clean and sound		
Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation					
<b>Colours</b>	Shades to customer's requirements				
<b>Product Code</b>	<b>20SGQ</b>				
<b>SG</b>	1.05 kg/lit (varies with colour)				
<b>Storage Conditions</b>	Store in dry, cool conditions and protect from frost				
<b>Shelf Life</b>	Minimum 12 months if stored as above in unopened containers				
<b>Flash Point</b>	23-60°C				

## Stokes OCF Semi-Gloss (QS-QF-QC)

<p><b>Surface Preparation</b></p>	<ul style="list-style-type: none"> <li>All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams</li> <li>Ideally blast clean to Sa2½ (ISO 8501-1:2007), surface profile 50-75 microns</li> <li>Where blast cleaning is not practicable, degrease overall and prepare any rusted areas to St2 minimum (ISO 8501-1:2007) without 'polishing' the steel surface</li> </ul>														
<p><b>Mixing</b></p>	<p>Must be mixed thoroughly by using a mechanical agitator before use. Agitate periodically to ensure paint remains homogeneous.</p>														
<p><b>Thinner</b></p>	<p>No.4 Thinner</p>		<p><b>Equipment Cleaner</b> No.4 Thinner</p>												
<p><b>Application Conditions</b></p>	<p>Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Paint temperature should ideally be at a minimum of 15°C.</p>														
<p><b>Application Methods</b></p>	<table border="1"> <thead> <tr> <th data-bbox="451 891 675 958">Method</th> <th data-bbox="675 891 940 958">Airless Spray</th> <th data-bbox="940 891 1166 958">Conventional Spray</th> <th data-bbox="1166 891 1339 958">Brush</th> <th data-bbox="1339 891 1489 958">Roller</th> </tr> </thead> <tbody> <tr> <td data-bbox="451 958 675 1012"></td> <td data-bbox="675 958 940 1012">Yes</td> <td data-bbox="940 958 1166 1012">Yes</td> <td data-bbox="1166 958 1339 1012">Yes</td> <td data-bbox="1339 958 1489 1012">Yes</td> </tr> </tbody> </table>					Method	Airless Spray	Conventional Spray	Brush	Roller		Yes	Yes	Yes	Yes
	Method	Airless Spray	Conventional Spray	Brush	Roller										
	Yes	Yes	Yes	Yes											
<ul style="list-style-type: none"> <li>Airless Spray: output fluid pressure at tip 1500-2000 psi, Tip Size 13-15 thou (0.33-0.43 mm)</li> <li>Hot Spray Application: suggested temperature of paint for hot spray is 30-50°C. Do not heat above 50°C as this will reduce intercoat adhesion of a second coat. If this temperature is exceeded, sand back before applying a second coat</li> <li>Conventional spray: thinning approx. 5-10% will be required, 55-65psi pressure and 1.8mm tip size recommended</li> <li>Application by brush/roller will result in a reduced film thickness and poorer cosmetic finish due to fast drying, and is recommended only for small areas of touch up/remedial work. See also Product Notes below</li> </ul>															
<p><b>Product Notes</b></p>	<ul style="list-style-type: none"> <li>Overcoating: may be overcoated with itself by spray after the Hard Dry times given. Overcoating by brush or roller with itself is not recommended, please consult Spencer Coatings for advice</li> <li>Some paints within this range may contain lead based pigments. Please refer to labels of individual paints for Risk &amp; Safety aspects of the shades</li> <li>*Colours such as yellows, reds and oranges have lower opacity, especially when produced using lead-free pigments. Two or three coats of these shades may be required, relative to only one coat of a grey or red oxide, so that yellows, bright reds and oranges may not be suitable as one coat systems</li> </ul>														
<p><b>Health &amp; Safety</b></p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Spencer Coatings.</p>														